

Research Article:

**EFFECTUL TRATĂRII TERMICE A
LEMNULUI DIN TRUNCHIURI TINERE DE
GORUN (*Quercus petrea* L.) ASUPRA
PROPRIETĂȚILOR PANOURILOR CU
FIBRĂ TRANSVERSALĂ**

**THE EFFECT OF THE HEAT
TREATMENT OF SESSILE OAK WOOD
(*Quercus petrea* L.) FROM YOUNG
TREES ON THE PROPERTIES OF
PANELS WITH TRANSVERSAL GRAIN**

Lidia GURĂU

Assoc.Prof.dr.eng. – TRANSILVANIA University in Brasov – Faculty of Wood Engineering
Adresa/Address: B-dul Eroilor nr. 29, 500036 Braşov, Romania
E-mail: rgurau@rdslink.ro

Mihaela CÂMPEAN

Prof.dr.eng. – TRANSILVANIA University in Brasov – Faculty of Wood Engineering
Adresa/Address: B-dul Eroilor nr. 29, 500036 Braşov, Romania
E-mail: campean@unitbv.ro

Alin OLĂRESCU

Lecturer dr.eng. – TRANSILVANIA University in Brasov – Faculty of Wood Engineering
Adresa/Address: B-dul Eroilor nr. 29, 50036 Braşov, Romania
E-mail: a.olarescu@unitbv.ro

Mihaela POROJAN

Lecturer dr.eng. – TRANSILVANIA University in Brasov – Faculty of Wood Engineering
Adresa/Address: B-dul Eroilor nr. 29, 50036 Braşov, Romania
E-mail: mporojan@unitbv.ro

Noemi MARTON

M.Sc. - TRANSILVANIA University in Brasov – Faculty of Wood Engineering
E-mail: nocy20@yahoo.com

BIBLIOGRAFIE / REFERENCES

- ANDERSSON, S., SERIMAA, R., VÄÄNÄNEN, t., PAAKKARI, T., JÄMSÄ, S., VIITANIEMI, P. (2005). X-Ray Scattering Studies of Thermally Modified Scots pine (*Pinus sylvestris*, L.). *Holzforschung* 59: 422-427.
- BENGTSSON, C., JERMER, J., CLANG, A. (2003). Glulam of Heat-Treated Wood-Delamination Test. In: Abstracts of the First European Conference on Wood Modification, Ghent, Belgium.
- CÂMPEAN M, GURĂU L, OLĂRESCU A. (2011). Effect of Heat Treatment upon Dimensional Stability and Static Bending Strength of Sessile Oak Wood. *PRO LIGNO* 7(2):46-55, ISSN-L 1841-4737.
- CIONCA, M., BĂDESCU, L., GURĂU, L., ZELENIU, O., OLĂRESCU, A. (2006b). Eco-Design Approach. A Research Regarding the Potential Use of Branches in New Wooden Products. In: Proc. of the International Conference on Environmentally Compatible Forest Products: ECOWOOD. 20-22 sept. 2006. Fernando Pessoa University. Porto. Portugal: 571-577.
- CIONCA, M., BĂDESCU, L., ZELENIU, O., GURĂU, L. (2006a). Panels Made of Crosscut Branches. *PRO LIGNO* 4(2):35-42.
- ESTEVEZ, B., VELEZ MARQUES, A., DOMINGOS, I., PEREIRA, H. (2008). Heat Induced Colour Changes of Pine (*Pinus pinaster*) and Eucalypt (*Eucalyptus globulus*) Wood. *Wood Science and Technology*. 42(5):369-384.
- ESTEVEZ, B.M., PEREIRA, H.M. (2009). Wood Modification by Heat Treatment: A Review. *BioResources* 4(1):370-404.
- FOREST PRODUCTS LABORATORY (1999). *Wood Handbook - Wood as an Engineering Material*. General Technical Report FPL-GTR-113. Madison, WI: U.S. Department of Agriculture, Forest Service, Forest Products Laboratory, 463 pp.
- GOVORČIN, S., SINKOVIČ, T., TRAJKOVIČ, J. (1998). Distribution of Properties in Use for Oak, Beech and Fir-Wood in Radial Direction. In: *Wood Structure and Properties*. Kurjatko, Stanislav ; Kudela, Jozef (ed). - Technica University in Zvolen: 30-38.

- HELINSKA-RACZKOWSKA, L. (1994). Variation of Vessel Lumen Diameter in Radial Direction as an Indication of the Juvenile Wood Growth in Oak (*Quercus petraea* Liebl). *Annals of Forest Science*, 51(3): 283-290.
- HIETALA, S., MAUNU, S., SUNDHOLM, F., JÄMSÄ, S., VIITANIEMI, P. (2002). Structure of Thermally Modified Wood Studied by Liquid State NMR Measurements. *Holzforschung* 56:522-528.
- KOLLMANN, F., FENGEL, D. (1965). Changes in the Chemical Composition of Wood by Heat Treatment. *Holz als Roh- und Werkstoff* 12:461-468.
- KOLLMANN, F.F.P., CÔTÉ, W.A.Jr. (1968). *Principles of Wood Science and Technology*. Vol. I. Solid Wood. Springer-Verlag, Berlin.
- KORKUT, S. (2008). The effects of heat treatment on some technological properties in Udulağ fir (*Abies bornmuelleriana* Mattf.) wood. *Building and Environment* 43:422-428.
- KORKUT, S., HIZIROGLU, S. (2009). Effect of heat treatment on mechanical properties of hazelnut wood (*Corylus colurna* L.). *Materials and Design* 30:1853-1858.
- KORKUT, S., KARAYILMAZLAR, S., HIZIROGLU, S., SANLI, T. (2010). Some of the Properties of Heat-Treated Sessile Oak (*Quercus petraea*). *Forest Products Journal* 60(5):473-480.
- OLĂRESCU, A., CÂMPEAN, M., GURĂU, L. (2011). Effect of Heat Treatment upon Dimensional Stability, MOE and MOR of Thin ($D_{max}=16$ cm) Sessile Oak Wood. *PRO LIGNO* 7(3):29-38.
- ÖZÇİFÇİ, A., YAPICI, F. (2008). Effects of Machining Method and Grain Orientation on the Bonding Strength of Some Species. *Journal of Materials Processing Technology*, 202 (1-3):353-358.
- PHUONG, L., SHIDA, S., SAITO, Y. (2007). Effects of Heat Treatment on Brittleness of *Styrax tonkinensis* Wood. *Journal of Wood Science*, 53:181-186.
- REID, R. (2005). Getting Serious about Oaks. *Agroforestry News*, 53:3.
- REITERER, A., SINN, G. (2002). Fracture Behaviour of Modified Spruce Wood: A Study Using Linear and Non-linear Fracture Mechanics. *Holzforschung* 56:191-198.
- ŞANDRU, M. (2011). *Metode statistice de optimizare a managementului educational*. Ed. Matrix, Bucuresti, ISBN 978-973-755-673-8.
- SHI, J., KOCAEFE, D., ZHANG, J. (2007). Mechanical Behaviour of Quebecwood Species Heat-Treated Using ThermoWood Process. *Holz-als-Roh und Werkstoff*, 65:255-259.
- WINDEISEN, E., STROBEL, C., WEGENER, G. (2007). Chemical Changes During the Production of Thermo-Treated Beech Wood. *Wood Science and Technology*, 41:523-536.
- ***ANSI A.208.2: 2002. Medium Density Fiberboard (MDF) for Interior Applications. Composite Panel Association.
- ***ASTM: 1997. Annual Book of ASTM Standards. Section 4., Vol. 04.10. Wood. American Society for Testing and Materials, West Conshohocken, PA.
- ***BS EN 13353: 2003. Solid Wood Panels (SWP)- Requirements.
- ***BS EN 310: 1993. Wood-Based Panels - Determination of Modulus of Elasticity in Bending and of Bending Strength.
- ***BS EN 318: 2002. Wood Based Panels. Determination of Dimensional Changes Associated with Changes in Relative Humidity.
- ***BS EN 322: 1993. Wood – Based Panels - Determination of Moisture Content.
- ***www.thermowood.fi/
- ***<http://org.elon.edu/econ/sac/anova.htm>